



CMS

CMS

CMS

CMS

CMS

## Chemical & Metallurgical Services

(NABL ACCREDITED LABORATORY)

T.S.No.63-A, SIDCO Industrial Estate, Ekkaduthangal, Chennai - 600 032, Tamilnadu INDIA. Phone: 91-44-2225 3863, Tele Fax: 91-44-2225 2944, Mobile: 9445067918 After Off. Hrs: 91-44-2245 1794 E-mail: cmslab81@gmail.com / rmdnayar@gmail.com



Page: 1 of 1

CMS

CMS

CMS

CMS

CMS

CMS

CMS

CMS

## TEST CERTIFICATE

CMS/LTR/T-10284-X/2015-16 Date : 07-03-2016

Test Report No. M/s. Assistant General Manager (Engg-Civil) - 1 Issued To

Airport Authority of India, Trichy International Airport,

Trichy Airport, Trichy - 620007.

No.AAI/TRY/Engg(C)/AR&MO)/RWY Painting/ 15-16/328. Dt: 02.03.2016. Your Ref. 1bottle. No. of Samples

:03-03-2016 Date of Receipt of Sample Physical Test .04-03-2016 Date of Testing

Nature of Test Nil **Enclosures** 

## TEST RESULTS

ASTM C 1648-06, ASTM D153.

Test Method

Sample Details me of work: A/R & M/O Civil working works at Trichy Airport during the year 2015-2016. SH:- Painting of Runway, Apron, Isolation By and Taxi way marking at Trichy Airport.

## Glass Beads (Plus 9)

	<u>TEST</u>		RESULT
(1)	Refractive Index		1.95
(2)	Specific Gravity	[E	4 25

(3) Sieve Analysis

<u>18:</u>	Sieve Designation		% by Retension
	1180 μm	8	0 %
	850 µm		0.26 %
	600 μm	2	43.20 %
	425 μm		71.35 %
	300 μm		98.60 %

\*\*\*\*END\*\*\*\*

R.M.D. NAYAR (Ex - Scientist - NML -CSIR) Technical Director

JRGICA

EXADITIVAÇÃ

CMS

CMS

CMS

Recognised & Approved Laboratory by Steel Authority of India Ltd. RITES LTD, Airports Authority of INDIA LTD. Defence Establishments, National & International Third Party Inspection Agencies & Many other State & Central Government Establishments.

Note:- This report relates only to the particular Sample submitted for test. Any correction not attested shall invalidate this certificate. Sample will be destroyed after 15 days from the date of issue of certificate unless instructed otherwise. Any complaints about this report should be communicated in writing within 7 days of the issue of this report. This report should not be reproduced wholly or in parts and cannot be used as evidence in a court of law and shall not be used in advertising media without prior permission in writing. Sample descriptions is not verified in all case and is given as described by the customers Samples are not drawn by us unless otherwise stated.

CMS Website: www.cmslab.in