

unclear conditions >>
clear indications

plus9beads® for Airport markings
High Index Glass beads from Swarco, Austria

TYPE

plus9beads®

300 – 850 µ acc. US spec. TT-B-1325 D Type III

DESCRIPTION

plus9beads are crystal-clear, transparent microspheres with a refractive index of min. 1.9. They are made of a high-quality pure melt and distinguish by high homogeneity and brilliance.

plus9beads are resistant against acids, calcium chloride, sodium sulfide, and water. There are no free crystalline silica; surface coatings are possible.

COATING

These beads are not coated. Coating can be done as per requirement.

TECHNICAL DATA

Test	Unit	Standard
Appearance	--	White powder
Size gradation	µ	300 - 850
Refractive Index	-	+1.9
Roundness	%	> 80 true spheres
Coating	-	-
*Specific weight	g/cm3	4.5 ± 0.3
*Bulk weight	g/cm3	2.5 ± 0.3
*Softening point	°C	over 1,000

***Tests will not be reported on COA.**

SIEVE ANALYSIS

Diameter (µm)	Standard Retain (%)
1180	0
850	0 - 5
600	25 - 45
425	65 - 85
300	95 - 100

APPLICATION

Thanks to their optical quality, **plus9beads** provide excellent retro reflectivity in various industrial and scientific applications, such as

- Reflective sheeting, airport runway markings
- User-specific applications in different fields e.g. reflective paints, decoration, filler material

STORAGE

Dry and sheltered

PACKAGING

Multi-layer paper bags of 25 kg net (standard), or as per requirement

Reference No: ITSC/G-00019	Issue Date: January 17, 2014	Prepared By: Dnyaneshwar Shekare	Date: 17/01/14
Revision No: 00	Revision Date: NA	Approved By: Deepali Nikam	Date: 17/01/14

Disclaimer: The information above is believed to be accurate and represents the best information currently available to us. However, we make no warranty of merchantability or any other warranty, express or implied, with respect to such information, and we assume no liability resulting from its use, handling and or from contact. Users should make their own investigations to determine the suitability of the information for their particular purposes. In no way ITS Coatings Pvt. Ltd be liable for any claims, losses, or damages of any third party or for lost profits or any special, indirect, incidental, consequential or exemplary damage, howsoever arising, even ITS Coatings Pvt. Ltd has been advised of the possibility of such damages

Head office

10-11, Creative Estate
N.M. Joshi Marg
Lower Parel (E)
Mumbai 400 011, INDIA
CIN No: U24233MH2012PTC229437

T: +91-22- 4054 6474
F: +91-22- 4054 6400
E: sales@itherm.in

Delhi Office

T: +91-11-41811881

Chennai Office

T: +91-44-26801165